



**TEST & EVALUATION REPORT**

July 18, 2015

**Report For:** Seaboard Asphalt Products  
 1194 Zinns Quarry Road  
 York, Pennsylvania 17404

**Attn:** Brandon Staub

**Email:** [brandon.staub@specialtyemulsionsinc.com](mailto:brandon.staub@specialtyemulsionsinc.com)

**Sample Data/Information:**


<b>Sample ID:</b> Bond-X Green Liquid	<b>Tank No:</b> 20	<b>Project #:</b> SEAB 01-02-01
<b>Received Date:</b> 7/14/15	<b>Batch No:</b> 57751	<b>Manufacturer:</b> Seaboard Asphalt Products

**OBJECTIVE:** Evaluate sample for properties listed below.


**DATA/RESULTS:**

PROPERTY	AASHTO / ASTM TEST METHOD	SPECIFICATIONS	RESULTS	
<b>Original Binder</b>				
VOC Content, % Distillate	437°F	ASTM 402M	Report	0
	500°F			0
	600°F			0
	680°F			0
	Total, %			0
Tag Flash Point, °F	T79	>400F	> 200	
Flash Point, COC, °F	D92		410	

**DISCUSSION:** See results in Table above.

Tested by:   
 \_\_\_\_\_  
 J. D'Angelo, Binder Lab Manager

Date: July 18, 2015

  
 \_\_\_\_\_  
 JV Martin, PhD, Senior VP

Date: July 18, 2015