



# MP-30 Seaboard Plastic Roof Cement

## Product Data Sheet

### Product Highlights

**Specification:**

ASTM D4586, Type I

**Solids:**

> 70 %

**Application Rate:**

25-45 Square Feet per Gallon.

**Recoat Time:**

8 Hours Minimum

**Application Temperature Range:**

No Limit

SEABOARD ASPHALT  
PRODUCTS COMPANY  
3601 Fairfield Road  
Baltimore, MD 21226

**Phone:** 1-800-536-0332  
or 1-410-355-0330

**Fax:** 1-410-355-5864

**Email:**  
sales@seboardasphalt.com

**Product Description:**

Seaboard Plastic Roof Cement is designed for ASTM D4586, Type I specification. This material is an asphalt cutback fortified with fillers and additives.

**Basic Uses:**

Seaboard Plastic Roof Cement is used to patch seams and seal joints in a variety of applications. This material acts as a water proofer for repairs.

**Storage and Limitations:**

- Do not heat container.

**Application:**

Seaboard Plastic Roof Cement must be applied to a surface free of foreign matter. This material is applied by trowel and should thoroughly cover and fill patching area. This product can be used year round.

**Coverage:**

25-45 Square Feet per Gallon.

**Composition and Safety:**

For complete safety information please review the Safety Data Sheet for this product.

Revision Date: 09/2016

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from law or patent implied.