



# LN-18 Clippership Polymer Modified Foundation Coating

## Product Data Sheet

### Product Highlights

**Specification:**

BOCA Section 1224

**Solids:**

> 68 %

**Application Rate:**

25 Square Feet per Gallon.

**Dry Time:**

4 to 8 Hours

**VOC Content:**

213 g/L, meeting applicable EPA, OTC, CARB, and SCAQMD Rules

SEABOARD ASPHALT  
PRODUCTS COMPANY  
3601 Fairfield Road  
Baltimore, MD 21226

**Phone:** 1-800-536-0332  
or 1-410-355-0330

**Fax:** 1-410-355-5864

**Email:**  
sales@seboardasphalt.com

**Product Description:**

Clippership Polymer Modified Foundation Coating is designed with asphalt and polymers for BOCA Section 1224 specification. This material is a polymer modified asphalt cutback for use as a waterproof coating. This material is impervious to water and remains pliable.

**Basic Uses:**

Clippership Polymer Modified Foundation Coating is used as a cold applied polymer modified asphalt membrane coating below grade to waterproof where water may cause deterioration or damage. This material can be used for private and commercial applications on metal tanks, metal and concrete pipes, block and poured foundations, and silos.

**Storage and Limitations:**

- Do not heat container.
- Protect metal container from weathering due to exposure.

**Application:**

Clippership Polymer Modified Foundation Coating must be applied to a dry surface free of foreign matter. This material penetrates and seals without priming and should be applied from top to bottom. This material can be brush, spray, or roller applied and is to be applied at a rate of 40 mil thickness. A two coat application is recommended. This product can be used year round.

**Coverage:**

25 Square Feet per Gallon.

**Composition and Safety:**

For complete safety information please review the Safety Data Sheet for this product.

Revision Date: 01/2016

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from law or patent implied.