



EM-50-TT / FGSL-40 Product Data Sheet

Product Highlights

Application Rate:

.05 to .10 gallon/square yard

Storage Temperature:

110°F Maximum

Application Temperature:

130°F to 160°F

“Break” Time:

Minimum 10 Minutes

Solids:

> 50%

SEABOARD ASPHALT
PRODUCTS COMPANY
3601 Fairfield Road
Baltimore, MD 21226

Phone: 1-800-536-0332
or 1-410-355-0330

Fax: 1-410-355-5864

Email:
sales@seboardasphalt.com

Product Description:

EM-50-TT is an anionic trackless tack coat emulsion that is used primarily as a tack coat or it is diluted 10% with water and used as a fog seal (FGSL-40). EM-50-TT is manufactured to meet applicable state specifications.

Storage and Limitations:

- Optimal storage for EM-50-TT is in a heated tank equipped with an agitator at a temperature below 110°F.
- Do not allow EM-50-TT to freeze.
- Avoid extreme overheating of EM-50-TT.
- See our Handling and Storage guide for more information.

Application and Coverage:

Depending on the surface being covered, EM-50-TT should be applied through a distributor at a rate of .05 to .10 gallons per square yard at a temperature of 130°F to 160°F. The maximum temperature allowable for application for EM-50-TT is 175°F.

Composition and Safety:

For complete safety information please review the Safety Data Sheet for this product.

Product Specifications:

<u>Specification</u>	<u>Minimum</u>	<u>Maximum</u>
Viscosity, seconds (T72)	0	100
Sieve Test, % (T59)	0.00	0.10
Residue by Distillation, % (T59)	50	-
Oil Distillate, % (T59)	0	3
Penetration (T49)	0	40

Revision Date: 09/2016

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from law or patent implied.

Revision Date: 09/2016

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to suitability of the contents. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from law or patent implied.

www.seaboardasphalt.com